

H. Behlen & Bro.

A Division of RPM Wood Finishes Group, Inc.

Product Data Sheet

Behlen Stringed Instrument Lacquer Aerosol

B104-1406

13 wt. ounce Aerosol Can

Product Description: Stringed Instrument Lacquer in an aerosol. Just as our Stringed instrument Lacquer in quarts and gallons, this aerosol is formulated specifically as a high quality finish for thin, flexible tone-woods such as those used on stringed instruments, made to withstand the expansion and contraction that is characteristic of the unique construction of stringed instruments. Vinyl Sealer is also flexible by nature. Therefore, it is the only sealer that should be used under Stringed Instrument Lacquer. This combination yields great sound and empowers luthiers to finish their handiwork with confidence.

Advantages:

1. Formulated for stringed instruments
2. Rubs to a beautiful high gloss finish
3. Resists cold checking

Characteristics:

Weight per gallon: 6.34 lbs/gal

Solids % (wt): 9.13

Solids % (vol): 5.77

Dry time: Air dry @ 72° F, 35% relative humidity

To handle and recoat: 1 to 2 hours

To rub: 1 to 4 weeks

VOC's (coating): 5.65 lbs/gal (678.72 g/l)

VOC's (material): 5.07 lbs/gal (608.56 g/l)

PWR Category: CCP

PWR Category Limit: 1.5

PWR of product: 1.002

VHAP's: 0.025 lbs VHAP's/lbs solids

Coverage: 7 to 10 square feet per can

Package Life: 3 years

All values theoretical; not intended to be exact QC specifications.

(Contains nitrocellulose resins, which tend to amber in color over time but does not affect coating performance)

HMIS: Health – 2, Flammability – 4, Reactivity – 0, Personal Protection – X

Directions: Seal with Behlen E-Z™ Vinyl Sealer, and highlight the guitar as desired. SHAKE WELL for one minute after agitator ball rattles. Apply full wet coats of Stringed Instrument Lacquer with overlapping strokes. Turn can upside down and press spray button for 5 seconds. Dry for at least 1 hour. Repeat application and dry cycle up to 3 times in one day. Dry overnight. Scuff sand. Repeat until 9-12 coats are applied. Wait at least 1 week after last application (4 weeks is best) and then rub as desired.

Safety and Other Precautions: Read MSDS for precautions before using product.

MSDS: If Material Safety Data Sheet is required, contact:

H. Behlen & Bros.

Division of RPM Wood Finishes Group, Inc.

P.O. Box 22000 Phone: 1-800-785-7781

Hickory, NC 28603 Fax: 1-800-721-1545

Website: www.hbehlen.com