



TECHNICAL DATA SHEET

Rev. 02 of 2014/05/23

GREENOL PLUS (impregnating finish)

code SO8211

TECHNICAL DATA

(based on room temperature of +23°C and 65% of relative air humidity)

Appearance	opalescent brown liquid
Viscosity	25" F4 ± 4" F4
Specific weight	0.88 ± 0.01
Impregnation time	10 – 15 minutes
Cautious foot traffic after	24 hours
Coverage (per coat)	15 – 20 m ² /litre
Abrasion resistance (abrasive wheel CS10, 1000 grs weight, 1000 revolutions)	30 mg
Abrasion resistance (abrasive wheel CS17, 1000 grs weight, 1000 revolutions)	44 mg
Thinning and tools cleaning	DILUENTE LINOLUX
Max. allowed thinning rate (Dir. 2004/42/CE)	50 %
VOC content %	51 %
VOC content g/lit	449 g/lit
Max. allowed VOC content (Subcat. f SB Exterior minimal build woodstain)	700 g/lit
(Canadian Directive DORS/2009-264 C.P. 2009-1535, category 32)	
◆ <i>Taber abramer test, abrasive wheel CS10, 1000 grs weight, 1000 revolutions</i>	

DESCRIPTION

GREENOL PLUS is an innovative product based on natural oils and resins, designed for wood protection and particularly suitable for wood floors. The use of the product, combined with GREENLINE products, gives the floors **good abrasion resistance**, which is obtained though no evident film is left on the surface, and enhances the natural beauty of the wood and its warm look.

GREENOL PLUS is suitable for **handmade application** on hardwood new-laid or new-sanded floors, factory-sanded and optionally brushed floors, as well as for **industrial production** of pre-finished wood floors.

GREENOL PLUS is available in transparent colourless version for satin sheen, and in the super white version.

GREENOL PLUS can be used even in combination with PRIMOL PLUS.

The application of GREENOL PLUS in combination with PRIMOL PLUS, according to the coverage above indicated, allows to achieve **Euroclass Classification Cfls1** for CE (norm UNI EN 14342) mark for oiled parquet on an industrial line (test report 0369/DC/REA/14_2).

HANDMADE APPLICATION

Application can be made by roller, brush, metal spatula or pad (sponge, paper, cloth).

- After final sanding or screening, vacuum and tack the floor thoroughly, then apply PRIMOL PLUS (or GREENOL PLUS), carefully spreading it as evenly as possible. If necessary, after 10-15 minutes remove excessive oil non absorbed by the wood with a cloth or a polyurethane foam rubber spatula (normally this is not necessary when the oil is applied by metal spatula). Within 20-30 minutes after application, before complete superficial drying, polish with a buffer at low speed, using a green pad, to make even the oil coat. After about 4 hrs, to remove any oil residue leaking out of the joining lines and the wood knots, it is advisable to polish again using a yellow or a white pad. **In case of strong colours, apply the product uniformly by pad and omit polishing to avoid colouring damage.** 20 - 24 hrs later, apply GREENOL PLUS finish according to the above described procedure and respecting the recommended coverage rate. Within 20-30 mins, brush with a green pad; after 3-4 hrs, in order to obtain a more uniform surface, polish using a white or a yellow pad.
- **Optionally** it's possible to apply 2 coats of GREENOL PLUS without primer, allowing 24 hrs break between coats and following the above-described procedure.
- **For a swift cycle** apply one coat of GREENOL PLUS by spatula and, with a 60-min. break, a second coat, if required. After the first coat, the oil could seem not completely absorbed within the indicated time range; in this case, polish the surface with a buffer at low speed, using a green pad, before applying the second coat. Within 20-30 mins from the end of application, polish again with a green pad. Finally, after at least 60 min., polish, if necessary, with a white or yellow pad.
- **For a white colour paving:** it advisable to add 5% of PRIMOL PLUS white to GREENOL PLUS



- **For an intense white colour paving:** it is advisable to use GREENOL PLUS Super White (perfectly miscible with the neutral version to get the desired shade of white)

NOTICE

- **Agitate the can before use!**
- **In any application method used, it is essential that the oils are applied in thin coats, using the recommended quantities. A too abundant coating could cause drying problems, particularly in the parquet joining lines (heads and edges) and the wood knots, where excessive oil could accumulate.**
- Do not apply at temperatures below +15 °C. Allow the products to reach room temperature before application.
- To avoid too rapid drying in summertime, it is advisable to thin the GREENOL PLUS oils by 5-10% with Carver DILUENTE LINOLUX thinner. Do the same when spreading is difficult.
- To obtain Euroclass Cfl on low density type of wood, a pre-treatment with FIRE PROTECT could be necessary.
- **Soak used rags and cloths in water immediately after use to prevent spontaneous combustion.**

INDUSTRIAL APPLICATION

GREENOL PLUS can also be applied at industrial level with spreading machines for the production of pre-finished parquet. **It is essential to apply thin coats (8-12 g/m² per coat) and to brush the boards or planks with natural fibre (such as tampico or sisal) polishing brushes right after each coating in order to help oil penetrate into the wood and to obtain the best drying.** The use of a hot-air tunnel (50-55° C for 100-120 sec.), when available, speeds up the drying.

Attention!

- Both the oil quantity to be applied and the drying time depend on the wood species. The higher is its absorption capacity, the greater the quantity and the quicker the drying.
- As a general rule, to obtain a good level finish we recommend overall (through application of several coats) quantities of 60-70 g/m² for porous and very absorbing wood species and of 50-60 g/m² for compact and not very absorbing ones.
- To obtain Euroclass Cfl it is necessary to apply 80-90 g/m² (Primol Plus + Greenol Plus). On low density type of wood, a pre-treatment with FIRE PROTECT could be necessary.

USE AND MAINTENANCE OF OILED WOOD FLOORS

24 hours after the impregnating treatment, the floor can be walked on cautiously. 7-10 days later, it can undergo the usual wearing and the regular maintenance can start. During this lapse of time, avoid laying rugs or dragging heavy pieces of furniture.

For cleaning and normal maintenance we recommend Carver DETEROL wood soap. Optionally, to obtain more protection and sheen, you may use Carver DERGOS, water-based cleaner and protective with a low wax content. For white paving use DETEROL white or DERGOS white.

For extraordinary maintenance and restoration of deteriorated places, first clean the floor thoroughly with DETEROL (to completely degrease you can use also Carver DETER PARQUET or NET PARQUET), then apply Carver CARSOL reconditioning oil (available in all versions of PRIMOL PLUS).

Dispose of excess product and empty containers properly.

If the original unopened containers are stored in a cool and dry place, the products will keep for at least 12 month

The information contained in this technical data sheet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.