

PAREO

Finishing oil for wooden decks and sidings
Easy restoration, no sanding required

Pareo is a non-film forming oil designed for decks, sidings, fences and other exterior wooden projects. Pareo colours, seals, waterproofs and prevents discolouration. Does not peel or blister and is easy to restore without sanding or stripping.



Number of Coats	2 coats
Drying Time	Water resistance: 6 hours Between coats: 12 to 24 hours, depending on temperature and humidity Careful traffic: 18 to 24 hours Full cure: 7 days
Available Colors	00 Colourless, 01 Cherry, 03 Medium Oak, 04 Charcoal, 06 Red Fox, 08 American Walnut, 11 Choco Wood, 13 Maple Brown, 15 Dark Oak, 17 Old Pine, 19 White, 20 Cappuccino, 21 Grey, 22 Natural, 23 Teak, 25 Burnt Wood, 26 Sand, 36 Smokey, 41 Ash Grey, 43 Driftwood, 44 Pale Walnut and 45 Pebble
Available Sizes	20 ml (Sample), 946 ml, 3,78 L and 18,9 L
Sheen	Matte 5 to 7 %
Applications	Exterior: Ideal for decks, siding, docks, fences, structures, garden furniture, doors, windows, play areas, flower boxes, and other outdoor wood projects.
Durability	Vertical surfaces: 2 to 6 years Horizontal surfaces: 1 to 3 years
Surface Types	Untreated wood Commercially treated dry wood (1 year) Restored wood (stained or oiled) Exotic wood
Advantages	Designed to withstand harsh Canadian climate Waterproofs wood surfaces Refreshes without stripping Prevents wood discolouration
Coverage	Average Coverage Sanded Wood: 500 to 800 ft ² /gal Rough-Cut Wood: 250 to 550 ft ² /gal
Compatibility	Can be covered with: Pareo Zero. Always perform a preliminary test to ensure product suitability and compatibility. Can be applied over: Oils and certain transparent and semi-transparent exterior oil-based stains. Can be covered with: Oils, varnishes, hybrid finishes, and paints.
Composition	Blend of vegetable oils, iron oxides, isoparaffin, lead-free and cobalt-free drier.
COV	437 g/L
Viscosity	22 sec. +/- 2 sec. with #4 Ford Cup (Clear)
Origin	Canada
Tools Cleaning	Prato-Verde Tools Cleaner and Thinner
Disposal of accessories and residues	After use, soak the rags in water or lay them flat to dry before disposal. Wipe off any liquid residue before recycling the container. Any leftover product should be brought to your municipality's eco-center.
Maintenance	For regular cleaning: PAREO CLEAN To revive shine and enhance protection every 2 to 3 months: PAREO MAINTENANCE For intensive cleaning (degreasing, deep cleaning), as needed: PAREO PREP For complete stripping: PAREO RESET
Storage and Shelf Life	Keep the product in a sealed container at a temperature between 10°C and 25°C for storage. Under these conditions, the product will maintain its quality for at least 5 years. If the product has been exposed to cold temperatures, allow it to return to room temperature for 24 hours before using.
Guarantee	Guarantee: Prato-Verde guarantees the quality of its products. They conform to the description provided in the technical data sheets and on the labels suitable for the intended use, in accordance with the instructions written by the company. However, since the manufacturer has no control over the circumstances, methods, and conditions of use, this guarantee only covers the high quality of Prato-Verde products.

Technical Specifications Preparation

1. Ensure the wood's moisture content is below 15%.
2. Do not apply in direct sunlight or at temperatures below 10 °C, or in very humid conditions.
3. For untreated wood or regular maintenance, clean the wood with PAREO PREP. For stripping stained or oiled wood, clean with PAREO RESET.
4. The wood must be clean, completely dry, and sanded with 60 or 80 grit sandpaper; change the sandpaper regularly to ensure good product penetration.
5. Dust off using a vacuum cleaner.
6. Perform a product test on a hidden surface and allow 24 hours between coats to validate the result, as it may vary depending on the type of wood used.

Technical Specifications Application

1. Thoroughly mix with a stick before and during application.
2. Apply the first coat generously until the wood is saturated using a staining brush or a staining pad.
3. After 5 to 10 minutes, if necessary, wipe the surface with clean POLYCOTTON RAGS to remove any excess oil.
4. Clean tools and accessories used with the TOOLS CLEANER AND THINNER, and soak oil-saturated cloths in water before disposing of them.
5. Allow drying for 12 to 24 hours.
6. If more than 24 hours have passed since the first application, lightly sand with 120-grit sandpaper before the second application.
7. Apply a second thin coat, repeating all previous steps.

Further Treatment

The greatest advantage of oil in wood treatment lies in its ease of maintenance and repair. The key to well-maintained oiled wood is prevention. The longer the interval between treatments, the longer the process will take. When PAREO CLEAN and PAREO MAINTENANCE products are no longer sufficient to keep your oiled wood in good condition, it's a sign that it's time to consider applying a new layer of oil.

Good general condition (Wood slightly dull):

1. Clean the wood with PAREO CLEAN.
2. Apply a coat of PAREO according to the product instructions.
3. No sanding or stripping required.

Good general condition (Stains or small damaged areas):

1. Sand the damaged area with 60 or 80-grit sandpaper.
2. Apply two coats of PAREO finishing oil to the sanded area following the product instructions.

Medium general condition (Slight discolouration, multiple stains, reduced resistance against water):

1. Clean the wood with PAREO PREP.
2. Apply one to two coats of PAREO according to the product instructions.
3. No sanding or stripping required.

Poor general condition (Severe discolouration, graying surface, no water resistance, many stains or damaged areas):

1. Clean the wood with PAREO RESET.
2. Sand the wood with 60 or 80-grit sandpaper.
3. Apply two coats of PAREO according to the product instructions.

Tips

Colours can be mixed to create unique shades. For application on rough-sawn wood, you can reduce the colour intensity by adding Pareo 00 - Colourless in a maximum ratio of 1:1. This step is not recommended for planed or sanded wood, as diluting the colour pigments would decrease UV resistance. Applying colours 00 - Colourless and 22 - Natural on sun-exposed surfaces requires more frequent maintenance. Colour 00 - Colourless provides an amber finish and enhances the wood grain. Colour 22 - Natural has a slightly whitened effect, helping to maintain the whiteness of light woods (pine, maple, cherry, spruce, beech, aspen, etc.). It's strongly recommended to perform a test beforehand on open-grain and coloured woods (oak, walnut, mahogany, elm, etc.).

WARNINGS

Keep out of reach of children. Keep away from flames or sparks.

DANGER OF COMBUSTION: Materials such as rags used with this product may begin to burn by themselves. After use, put rags in water or lay flat to dry, then discard.